

Facestock

White, machine coated, semi-gloss appearance with 30% recycled content.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)

Basis Weight	78 g/m ²	ISO 536
Caliper	64 µm	ISO 534

Adhesive

A general purpose removable, rubber based adhesive.

Liner

BG40 brown, supercalendered glassine paper.

Basis Weight	53 g/m ²	ISO 536
Caliper	46 µm	ISO 534

Laminate

Total Caliper	128 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	5 N/25mm	FTM 9 Glass
Peel Adhesion 90°	2.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	-20 °C	
Service Temperature	-40 °C to 70 °C	

Adhesive Performance

The adhesive is suitable for general application on a wide range of substrates, featuring good initial tack and adhesion combined with excellent removability. Remark: Application to porous substrates such as paper and board, or prolonged exposure to UV light may adversely affect clean removability.

Applications and Use

30% post consumer waste recycled material suitable as a general labelling material with very good sustainability credentials.

Conversion and Printing

Suitable for solid and halftone images and text printing by letterpress, flexo (UV and waterbased) offset and screen processes. Hot and cold foil stamping, varnishing and variable imprinting with thermal transfer are also suitable for this product. Being produced from 30% post consumer waste paper, there is a possible higher incidence of impurities in the product compared to virgin fiber products.

Compliance and Approvals

The adhesive R5100 is suitable for contact with dry, non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AA738

Fasson®

rMC PRIMECOAT FSC
R5100-BG40BR



RMC PRIMECOAT FSC

R5100

BG40BR



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.