

### Facestock

A matt white PEHD film with paper like coating for matrix and thermal transfer printing.

Basis Weight	75 g/m <sup>2</sup>	ISO 536
Caliper	95 µm	ISO 534

### Adhesive

A special purpose rubber hotmelt adhesive, featuring high tack and final peel adhesion with very high coat weight.

### Liner

BG45 white FSC is a supercalendered glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	69 g/m <sup>2</sup>	ISO 536
Caliper	60 µm	ISO 534

### Laminate

Total Caliper	202 µm±10%	ISO 534
---------------	------------	---------

### Performance Data

Initial Tack	35 N/25mm	FTM 9 Glass
Peel Adhesion 90°	21 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service Temperature	-20 °C to 70 °C	

### Adhesive Performance

TS8000 uses an aggressive formulation developed for labelling rubber with irregular and curved surfaces. It withstands typical chemicals used by tyre manufacturers, such as mould release agents or components migrating from the rubber.

### Applications and Use

Product gives very good performance in thermal transfer printing as well as dot-matrix and conventional pre-printing techniques. The topcoating has compatibility with a wide range of wax, wax/resin and resin based thermal transfer ribbons and is capable of producing high resolution barcode prints. The base film has good rigidity for larger label handling. Applications include medium life durable tracking labels in outdoor environments eg. chemical drum labels, stretch and shrink wrapped pallet labels where recycling may be required.

### Conversion and Printing

The absorbent top-coat provides a 'paper like' surface for conventional preprinting. Due to the extensible nature of the face, care should be taken with die-specification. Sharp dies are essential. Material shows very good register stability on press and flat bed conversion. However, rotary and magnetic dies need additional care.

Note: this product contains a very aggressive adhesive. If the product is without SGP (Special Gum Pattern), adhesive ooze on the sides of the slit rolls can occur. To minimize this risk it is highly recommended to order this material with an adhesive-free zone on each side of the slit rolls (with SGP / gumpattern). Please contact your sales representative for further details.

## AF081

### Fasson®

#### PE80 DATA MATT WHITE TS8000DEC-BG45WH FSC



PE80 DATA MATT WHITE

TS8000

BG45WH FSC



The mark of  
responsible forestry

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Compliance and Approvals

Adhesive TS8000 has attained the two star certification for biobased content according to EN 16640, meaning that TS8000 contains certified Biobased Carbon Content of at least 40%. (TÜV AUSTRIA licensee number: S0259)



\*The OK biobased certification is only applicable to the adhesive TS8000.

### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## Appendix

### Compliance with BS 5609

This material complies with BS 5609, Section two, Marine Immersion Test.

## Thermal Transfer Printing:

### Printability – Physical Resistance

Ribbon	Settings		Print Quality	ANSI Grade	Scratch resistance	Tape resistance
	speed	energy				
Armor AXR7+	5	30	++	A	++	-
Armor AXR8	5	30	++	A	++	+
DNP R300	5	30	+	A	++	++
DNP R550	5	30	--	C	+	+
limak PM255	5	20	++	A	--	+
limak SP330	5	30	++	A	++	++
Ricoh B110A-X2	5	20	++	A	-	+
Ricoh B120EC	5	30	-	B	++	++
Ricoh B110CR	5	30	+	A	++	++

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty

++: excellent +: good o: acceptable -: poor

Tests were performed with the printer Zebra 140XI3.

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.