

#### Facestock

A gloss clear polyester film with a print treated coating.

Basis Weight	51 g/m <sup>2</sup>	ISO 536
Caliper	36 µm	ISO 534

#### Adhesive

A luminescent, acrylic based permanent adhesive.

#### Liner

A clear polyester liner. The polyester liner giving optimum smoothness to the adhesive layer.

Basis Weight	50 g/m <sup>2</sup>	ISO 536
Caliper	36 µm	ISO 534
Transparency	99 %	DIN 53147

#### Laminate

Total Caliper	88 µm±10%	ISO 534
---------------	-----------	---------

#### Performance Data

Initial Tack	12 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-40 °C to 90 °C	
Laetus Value	minimum 8	

#### Adhesive Performance

S697 LUM is a clear, luminescent adhesive for use with clear filmic face and liner materials.

#### Applications and Use

A glass clear label of very good quality for use in harsh environments where good resistance to elevated temperatures and chemicals as well as good durability is required.

The robust film liner allows for consistent, snap free, application on high speed lines. As liner is transparent, the applicator must detect the print itself or registration marks must be provided on either face or liner.

#### Conversion and Printing

The ink receptive coating allows good wettability and ink adhesion with letterpress, offset, flexo, gravure and hot foil stamping. Precautions should be taken to avoid build-up of static electricity.

Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner).


#### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## AJ141

### Fasson®

#### PET36 TOP CLEAR S697 LUM-PET36



PET36 TOP CLEAR

S697 LUM

PET36

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

## Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.